

Nylon Tubing Series T/TIA RoHS

For general pneumatic tubing, Nylon tubing

Max. Operating Pressure



How to measure the minimum bending radius.



At a temperature of 20°C, bend the tubing into a U shape. Fix one end and gradually move the other end closer. Measure 2R at the point where the outside diameter's rate of change is 10%.

Precautions

⚠ Caution

- 1. Applicable for general industrial water. Please consult with SMC if using other kinds of fluid. Surge pressure must be under the max. operating pressure. If the surge pressure exceeds the maximum operating pressure, it will result in damage to fittings and tubes.
- 2. Please exercise caution when using this item in a clean room. There is a possibility of plasticizer and other materials precipitating on the tube surface and detracting from the cleanliness level of the room.

Model

 \bullet — 20 m roll \Box — 100 m roll (T1613 is reel.)

			Tubing size											
				Metr	ic size	(Seri	es T)			In	ch siz	e (Ser	ries TI	A)
Mod	el	T0425	T0403	T0604	T0645	T0806	T1075	T1209	T1613	TIA01	TIA05	TIA07	TIA11	TIA13
Tubing O.D). (mm)	4	4	6	6	8	10	12	16	3.18	4.76	6.35	9.53	12.7
Tubing I.D.	(mm)	2.5	3	4	4.5	6	7.5	9	13	2.18	3.48	4.57	6.99	9.56
Black (B)		-	-							-	-	-	-	-
White (W)		<u></u>	+		+			<u></u>	<u></u>	-	-	-	-	-
Red (R)		-	-	+	+	+	+	+					+	
Blue (BU)		-		+		-	+	-						
Yellow (Y)		-		+		-	-	-						
Green (G)		-	-	-	-	-	-	-	-		-		+	-
		5/32 "				5/16"				1/8 "	Nomin 3/ ₁₆ "	al size	3/8 "	1/2 "
Specific	ations	5								Nominal size (mm) 3.2				
Fluid							Α	ir/Wat	er					
	20°C or less	_	2.0	3.0	2.0	2.0	2.0	2.0	1.6	2.3	2.3	2.3	2.3	2.3
	40°C	2.3	1.4	2.1	1.4	1.4	1.4	1.4	1.1	1.6	1.6	1.6	1.6	1.6
pressure Note 1)	60°C	1.65	1.0	1.5	1.0	1.0	1.0	1.0	0.8	1.15	1.15	1.15	1.15	1.15
	80°C	1.35	0.8	1.25	0.8	0.8	0.8	0.8	0.65	0.95	0.95	0.95	0.95	0.95
Applicable fitting	100°C	1.2	0.75 One-to	1.1	0.75	0.75	0.75	0.75	0.6	0.85	0.85 s. Min	0.85		0.85
Min. bending	Min. bending radius	13	20	24	30	40	50	60	100	15	25	30	50	65
radius	Ponding value													

Note 1) Be sure to operate under the maximum operating pressure conditions using the lower maximum operating specification of either the tubing or fittings.

75 12 20 23

-40 to +100°C, Water: 0 to +70°C (No freezing)

Nylon 12

40 48

Note 2) Mount an inner sleeve when using metal One-touch fittings in high-temperature environments of

60°C or more. Use self-align fittings at a temperature of 60°C or less. Note 3) The minimum bending radius is the representative value measured as shown in the left figure.

• Use a tube above the recommended minimum bending radius.

Bending value

(Reference)

Operating temperature Note 1

10


15 18 23 30 40 45

(mm) Note 3)

Material

The tubing may be bent if used under the recommended minimum bending radius.
 Therefore, refer to the refraction value and make sure that the tubing is not bent or flattened.

• Please note that the refraction value is not warranted because of the value when 2R is measured by the method in the left figure if the tubing is bent or flattened, etc.






Soft Nylon Tubing Series TS/TISA

For general pneumatic tubing Model

lacksquare — 20 m roll $\ \square$ — 100 m roll (TS1612 is reel.)

RoHS



Pliable soft nylon tubing

2.2 TS0425	
g 2.0 100425	
© 2.0 ≥ 1.8 TS0604	
§ 1.6	
9 1.6 1.4 0 1.2	
a 1.2	
Other than	
TS0425, TS0604	
1.0 Utter trial TS0425, TS0604 TS0425, TS0604	
3 0.4	
× 0.4 W 0.2	
2 0.0	
-40 -20 0 20 40 60 80	100
Operating temperature °C	

⚠ Caution

- 1. Compatible with water due to a change in materials. Compatible fluid types are printed on the tube body for differentiation, so please be sure to check this. Note) If using the previous TS/TISA series with "water", the tube may shrink and cause air leakage or the tube may fall out.
- 2. The products which changed the material are applicable for general industrial water. Please contact SMC if using other kinds of fluid. Surge pressure must be under the max. operating pressure. If the surge pressure exceeds the maximum operating pressure, it will result in damage to fittings and tubes.
- 3. Please exercise caution when using this item in a clean room. There is a possibility of plasticizer and other materials precipitating on the tube surface and detracting from the cleanliness level of the room.

At a temperature of 20°C, bend the tub-

ing into a U shape. Fix one end and

gradually move the other end closer.

Measure 2R at the point where the out-

side diameter's rate of change is 10%.

			Tubing size									
				ric size						e (Serie		
	1odel	TS0425	TS0604	TS0806	TS1075	TS1209	TS1612		TISA05		TISA11	TISA13
	O.D. (mm)	4	6	8	10	12	16	3.18	4.76	6.35	9.53	12.7
Tubing	g I.D. (mm)	2.5	4	6	7.5	9	12	2.18	3.48	4.57	6.99	9.56
Bla	ck (B)	-	_•	_•	- •-	-	_•	-	-	-	-	-
Whi	ite (W)	- •-		- •-				-	-	•	-	
Rec	d (R)	-	•	-	-	•	-	-	-			+
Blu	e (BU)	+	•	•	•	•						+
Yell	low (Y)	+	•	•	•	•						-
Gre	en (G)	-	•	•	•	•						+
									Nomina	al size (i	inch)	
		5/32 "		5/16"				1/8 "	3/16"	1/4 "	3/8 "	1/2 "
								Nominal				
_								size (mm)				
Spec	ification	S						3.2				
Fluid		Air/Water Note 1)										
Max.	20°C or less	2.0	1.7	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
operating	40°C	1.4	1.2	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
pressure	60°C	1.0	0.85	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65
MPa	80°C	0.8	0.65	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
Note 2)	100°C	0.6	0.45	0.35	0.35	0.35	0.4	0.35	0.35	0.35	0.35	0.35
	le fittings Note 2) 3)											
Min. bending	Min. bending radius	15	23	45	55	65	90	18	27	30	55	65
	Bending value (Reference)	12	17	34	42	50	70	12	15	23	42	50
Operating temperature Note 2) —40 to +100°C, Water: 0 to +50°C (No freezing)				g)								
Mater	rial					Ny	lon 12					
	Note to Defends the Whiteless (Child											

Note 1) Refer to the "Printing/Fluid".

Note 2) Be sure to operate under the maximum operating pressure and operating temperature conditions using the lower specifications of either the tubing or fittings.

Note 3) Mount an inner sleeve when using metal One-touch fittings in high-temperature environments of 60°C or more. Use self-align fittings at a temperature of 60°C or less.

Note 4) The minimum bending radius is the representative value measured as shown in the left figure.

*Useatubeabovetheminimumbendingradius.


*Thetubingmaybebentifusedundertheminimumbendingradius.Therefore,refertothebendingvalueandmake sure that the tubing is not bent or flattened.

*Pleasenotethatthebendingvalueisnotwarrantedbecauseoftherepresentativevaluewhen2Rismeasuredby the method in the left figure if the tubing is bent or flattened, etc.

Printing/Fluid

	Print code					
Previ	Previous SMC TS 0604 SOFTNYLON 6 x 4					
NE	W	● SMC TS 0604 SOFTNYLON 6 x 4	Air/Water			

How to Order



Made to Order

Fixed end

How to measure the minimum bending radius

(Please contact SMC for specifications in detail, dimensions, delivery and specifications other than those mentioned above.)

100 m reel Metric size and Inch size except ø16: Suffix "-X3" to the end of part number. Ex.) TS0425R-100-X3 Longer length reel Metric size: Suffix "-X3" to the end of part number. Ex.) TS0425G-500-X3

20 m roll Inch size: Suffix "-X4" to the end of part number. Ex.) TISA01BU-20-X4

Made to Order Availability

		,	'									
Part no.	Length Model	TS0425*	TS0604*	TS0806*	TS1075*	TS1209*	TISA01*	TISA05*	TISA07*	TISA11*	TISA13*	Color
	100 m reel	0	0	0	0	0	0	0	0	0	0	Black, White.
ХЗ	150 m reel				0							Red, Blue,
Λ3	200 m reel			0								
	500 m reel	0	0									Yellow, Green
X4	20 m roll						0	0	0	0	0	Red, Blue, Yellow, Green

Soft Polyurethane Tubing

Series TUS




Suitable for piping in confined spaces **Extremely flexible Soft Polyurethane Tubing**

TUS related accessories **Inner Sleeve**

Series TJ

Reinforces soft polyurethane tubing. Insert an inner sleeve into soft polyurethane tubing when used with a One-touch fitting



Part No.	Applicable tube model	Length
TJ-0425	TUS0425	18
TJ-0604	TUS0604	19
TJ-0805	TUS0805	20.5
TJ-1065	TUS1065	23
T.I-1208	TUS1208	24

Specifications

Material	C2700T (Nickel plated)
Wall thickness	0.2mm

▲ Precautions

1)Use nylon or polyurethane tubing for general industry water to prevent the tubing from coming out or bursting due to possibility of surge pressure generation.

- 2The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rise which may burst the tubing.
- 3The value of the min. bending radius is at a temperature of 20°C. Higher temperatures allows the tubing to bend more.
- 4 Use inner sleeve taking the removing force into consideration when used with Onetouch fittings.

Series Table				●: 20m rol	II □: 100m roll
Model	TUS0425	TUS0604	TUS0805	TUS1065	TUS1208
Tube O.D. (mm)	4	6	8	10	12
Tube I.D. (mm)	2.5	4	5	6.5	8
Black (B)	—	<u> </u>	<u> </u>	<u> </u>	<u> </u>
White (W)	—		-	-	
Red (R)	—	-	-	-	
Blue (BU)	<u> </u>	<u> </u>	<u> </u>	<u> </u>	<u> </u>
Yellow (Y)	—		-	-	
Green (G)	—				
Opaque (N) (1)					
Yellow brown (YB)					
Specifications					

Specifications

Fluid	Fluid			Air						
Max. operating pressure				0.6MPa at 20	°C					
Burst pressure			Refer to burst pressure characteristics curve.							
Applicable tube	On	One-touch fitting, Insert tube fitting, Hose nipple (3)								
Min. bending rad	8	15	15	22	29					
Operating temper	-20 to +60°C (No freezing)									
Material		Polyurethane								
Tube drawing strenght N (Using One-touch fitting)	Without inner sleeve	15	60	60	85	110				
	With inner sleeve	80	230	250	300	480				
_										

Note1) Not clear but opaque due to material.


Note2) Min. bending radius is measured as shown in the figure below.




Bend the tube into U-form at a temperature of 20°C. Fix one end and close loop gradually. Measure 2R when the tube breaks or is crushed.

Note3) Always use inner sleeve (Series TJ) in safety circuit or critical area.

Burst Pressure Characteristics Curve








Hard Polyurethane Tubing

Series TUH ROHS






Maximum effective area increased nearly 44%

TUH/Standard Type

(Compared to polyurethane tubing TU0805: O.D. 8mm, length 1m)



Tubing inside diameter comparison (mm)								
Tu	ubing O.D. (ØD1)	4	6	8	10	12		
Tubing I.D. (ØD2)	TUH/Standard type	2.8	4.4	5.8	7.3	8.8		
	TUH/High pressure type TU	2.5	4	5	6.5	8		

Operating pressure 1.0MPa (at 20°C) **TUH/High Pressure Type**

Has the same operating pressure as series TS soft nylon tubing, and a bending radius equivalent to series TU polyurethane tubing.

Can be restored even after folding

Restoration is outstanding compared to nylon tubing, leaving no creases from folding.




Hard Polyurethane Tubing/Standard Type

Series TUH ROHS







At a temperature of 20°C bend the tubing into a U shape. Then with one side fixed, gradually close the other side and measure 2R at the point where the tubing folds or flattens, etc.

Series

 \bullet – 20m bundle \square – 100m bundle

Model	TUH0428	TUH0644	TUH0858	TUH1073	TUH1288
O.D. mm	4	6	8	10	12
I.D. mm	2.8	4.4	5.8	7.3	8.8
Black (B)					
White (W)	—	<u> </u>	<u> </u>	<u> </u>	—
Blue (BU)	-	<u> </u>	<u> </u>	<u> </u>	—
Translucent (N)	-	<u> </u>	<u> </u>	<u> </u>	—
Specification	ons				

Fluid		Air Note 1)							
Max. operating pressure (at 20°C)		0.8MPa Note 2)							
Min. bending radius mm	10	18	24	30	36				
Burst pressure	Refe	Refer to the burst pressure characteristics curve.							
Operating temperature	−20 to 60°C								
Material			Polyurethane	1					

Note 1) Consult SMC regarding other fluids.


Water cannot be used due to the occurrence of hydrolysis.


Note 2) The maximum operating pressure is the value at 20°C. Refer to the burst pressure characteristic curve for other temperatures.

Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.

Note 3) The minimum bending radius is measured at 20 $^{\circ}\text{C}$ using the method shown in the figure at the left. At higher temperatures, breakage or flattening, etc., may occur at more than the minimum bending radius.

Burst Pressure Characteristic Curve and Operating Pressure








Hard Polyurethane Tubing/High Pressure Type

Series TUH ROHS







At a temperature of 20°C bend the tubing into a U shape. Then with one side fixed, gradually close the other side and measure 2R at the point where the tubing folds or flattens, etc.

Series

■ – 20m bundle □ – 100m bundle


Model	TUH0425	TUH0604	TUH0805	TUH1065	TUH1208
O.D. mm	4	6	8	10	12
I.D. mm	2.5	4	5	6.5	8
Black (B) White (W) Blue (BU) Translucent (N)					
Specification	ons				
Eluid			Air Note 1)		

Fluid	Air Note 1)							
Max. operating pressure (at 20°C)		1.0MPa Note 2)						
Min. bending radius mm	10	10 15 20 27 35						
Burst pressure	Refer	Refer to the burst pressure characteristics curve.						
Operating temperature	−20 to 60°C							
Material		Polyurethane						
temperature								

- Note 1) Consult SMC regarding other fluids.
 - Water cannot be used due to the occurrence of hydrolysis.
- Note 2) The maximum operating pressure is the value at 20°C. Refer to the burst pressure characteristic curve for other temperatures.
 - Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.
- Note 3) The minimum bending radius is measured at 20°C using the method shown in the figure at the left. At higher temperatures, breakage or flattening, etc., may occur at more than the minimum bending radius.

Burst Pressure Characteristic Curve and Operating Pressure

7 MPa **Burst pressure** 3 Maximum operating pressure -20 40 Operating temperature °C







Series TUH/Specific Product Precautions 1

Be sure to read before handling.


Precautions on Usage

⚠ Caution

- Water cannot be used due to the occurance of hydrolysis.
 Use nylon or polyurethane tubing for general industrial water.
 Furthermore, consult SMC regarding use with any fluids other than air.
- The maximum operating pressure is the value at 20°C. Refer to the burst pressure characteristic curve for other temperatures.
 Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.
- The minimum bending radius indicates the value at which the tubing will fold at a temperature of 20°C. At higher temperatures, the tubing may fold at more than the minimum bending radius.
- Store away from direct sunlight in a location at no more than 40°C.



FEP Tubing (Fluoropolymer)



Heat resistance: 20

It changes according to the operating pressure. Refer to the graph of the max. operating pressures on page 1.

4 Colour variations



8 Size variations

Metric size: ø4 to ø12

 Applicable fittings

One-touch fittings (Series KQ2,KJ) Miniature fittings (Series M,MS) (Hose nipple type) **Insert fittings (Series KF)** High Purity Fluoropolymer fittings (Series LQ)

SMC

Series TH

Applications

General pneumatic piping Semiconductor

Medical care Automobile

 Certified to current **Food Sanitation** Legislation

Ministry of Japanese Health and Safety, directive #370,1959


FEP Tubing (Fluoropolymer)

Series TH






How to measure the minimum bending radius.



At a temperature of 20°C, bend the tubing into a U shape. Fix one end and gradually move the other end closer. Measure 2R at the point where the outside diameter's rate of change is 5%.

Max. Operating Pressure



Note) The maximum operating pressure varies dependant on the I.D. bore size even if the O.D. is the same.

Series ●-20m roll □-100m roll Metric size TH0402 TH0425 TH0604 TH0806 TH1075 TH1008 TH1209 TH1210 Model Tubing O.D. (mm) Tubing I.D. (mm) 2 2.5 4 6 7.5 10 Colour Symbol Ν Translucent R Red (Translucent) BU Blue (Translucent) Black (Opaque) В Inch nominal size Inch nominal size 5/16" 5/321 **Specifications**

Fluid	Note 4)		Air, Water Note 1), Inert gas						
Applicable fittings	Note 2)	Fluorop	e-touch fittings: Series KQ, KJ Insert fittings: Series KF propolymer fittings: Series LQ ature fittings: Series M, MS (Hose nipple type)						
Max. operating pr	ressure		Ref	er to belo	ow "Max.	Operatin	g Pressure."		
Min. bending radius (mm)	Note 3)	15	20	35	60	95	100	130	
Operating temporary	Note 4) erature	Air,	Air, Inert gas: -20 to 200°C Water: 0 to 100°C (No freezing)					zing)	
Material		FEP (Fluorinated Ethylene Propylene Resin)							

Note 1) When using a fluid in liquid form, the surge pressure must not exceed the maximum operating pressure. A surge pressure higher than the maximum operating pressure can cause breakage of the fittings, or rupture of the tubing. Furthermore, an abnormal temperature increase due to adiabatic compression can also result in ruptured tubing. Note 2) Do not use in locations where the FEP tubing will move.

Be sure to operate under the maximum operating pressure conditions using the lower maximum operating specification of either the tubing or fittings.


After long term use or under high temperatures, some fittings leakage may occur due to material deterioration with age. Perform periodic inspections, and if any leakage is detected, replace with a new product immediately. (Refer to maintenance part of "Tubing Precautions 1" on the page 7-156.)

Refer to Best Pneumatics 4 in "Fittings and Tubing" for all other precautions.

For High Purity Fluoropolymer, refer to the precautions of CAT. ES70-17, "High Purity Fluoropolymer Fittings & Tubing.

Note 3) Minimum bending radius is measured as shown left as representative values.

Allow extra length when piping since the tubing may crush if bent more than the min. bending radius. Note 4) Consult SMC if using any other fluids.







Chemical Resistance of the Fluoropolymer FEP Material

Chemicals in this table are inactive against FEP material Note 1), however physical properties may be effected by temperature or pressure change.

Please make sure that operating conditions do not cause problems since the use of FEP tubing under chemical environment is unsecured.

2-nitro-2-methyl propanol

2-nitrobutanol

Pentabasic benzamide

N-butylamine N-octadecanol N-butyl acetate O-cresol

Di-isobutyl adipate Acetophenone

Acetophenone
Acetone
Alniline
Abietic acid
Sulphuric chloride

Isooctane

Liquid ammonia
Ethyl alcohol
Ethyl ether
Ethylene glycol
Ethylenediamine

Zinc chloride
Aluminum chloride
Ammonium chloride
Calcium chloride
Sulphuric chloride
Iron chloride (III)
Benzoyl chloride

Magnesium chloride Hydrochloric acid Chlorine (absolute)

Aqua regia Ozone

Hydrogen peroxide Natrium peroxide

Gasoline
Permanganate
Formic acid
Xvlene

Chromic acid
Chlorosulfonic acid

Chloroform

Paraffinum liquidum

Allyl acetate Ethyl acetate Potassium Butyl acetate Sodium hypochlorite Carbon tetrachloride

Dioxane

Cyclohexanone
Cyclohexane
Dimethyl ether
Dimethylsulfoxide

Dimethylformamide Bromine

Deionized water Nitric acid Mercury

Ammonium hydroxide Potassium hydroxide

Sodium hydroxide

Cetane

Soap, detergent
Dibutyl sebacate
Diethyl carbonate
Tetrachloroethylene
Tetrahydrofuran
Tetrabromoethane
Triethanolamine
Trichloroethylene
Trichloroacetic acid

Toluene Naphtha Naphthalene Naphthol Lead

Carbon dioxide Nitrogen dioxide Nitrobenzene Nitromethane Perchloroethylene Perphloroxylene

Unsymmetrical dimethylhydrazine

Hydrazine Pinene Piperidine

Glacial acetic acid (Acetic acid)

Pyridine
Phenol
Phthalic acid
Dybutyl phthalate

Dimethyl phthalate Hydrofluoric acid Naphthalene fluoride

Nitrobenzene fluoride

Furan

Hexachlorethane

Hexane

Ethyl hexanoate Phenylcarbinol Benzaldehyde Benzonitrile Borax Boric acid

Formic aldehyde (Formalin)

Acrylic anhydride
Acetic anhydride
Methacrylic acid
Allyl methacrylate
Vinyl methacrylate
Wethyl alcohol
Methyl ethyl ketone
Methylene chloride
Sulphuric acid
Phosphoric acid
Iron phosphate (III)
Tri-n-butyl phosphate
Tricresyl phosphate

Note 1) "Inactive in chemistry terminology" means - not to cause any chemical reaction.

Reference cited: Teflon®, the fluoropolymer handbook, Manual for the chemical applications of Teflon®. Du Pond-Mitsui Fluorochemicals Co., Ltd.

Teflon® is a registered trademark for the fluoropolymer produced by E.I du Pond de Nemours & Company (Inc.) and Du Pond-Mitsui Fluorochemicals Co., Ltd.



Selection

A Warning

1. Confirm the specifications.

The products appearing in this catalogue are designed for use only in compressed air systems (including vacuum).

Do not use outside the specified ranges of pressure, temperature, etc., as this may cause damage or malfunction. (Refer to specifications.)

SMC cannot assure the product quality when fluids other than air, water and inert gas are used.

Consult with SMC for details.

2. In case of using the product for medical care

This product is designed for use with compressed air system applications for medical care purposes. Do not use in contact with human bodily fluids, body tissues or transfer applications to a human living body.

⚠ Caution

 Do not use in locations where the connecting threads and tubing connection will slide or rotate. The connecting theads and tubing connection will come apart under these conditions.

Use rotary type one-touch fittings (Series KS, KX) in cases where sliding or rotation will occur. Only air can be used as the operating fluid, when using rotary type one-touch fittings.

- Use tubing at or above the minimum bending radius. Using below the minimum bending radius can cause breakage or flattening of the tubing.
- Never use the tubing for anything flammable, explosive or toxic such as, gas, fuel gas, or cooling mediums, since the contents can penetrate outward.

Mounting

⚠ Caution

- 1. Before mounting confirm the model and size, etc. Also, confirm that there are no blemishes, nicks or cracks in the product.
- 2. When tubing is connected, consider factors such as changes in the tubing length due to pressure, and allow sufficient leeway.
- 3. Mount so that fittings and tubing are not subjected to twisting, pulling or moment loads. This can cause damage to fittings and flattening, bursting or disconnection of tubing, etc.
- Mount so that tubing is not damaged due to tangling and abrasion.
 This can cause flattening, bursting or disconnection of tubing, etc.

Piping

⚠ Caution

1. Preparation before piping

Before piping is connected, it should be thoroughly blown out with air (flushing) or washed to remove chips, cutting oil and other debris from inside the pipe. Do not allow chips of the piping thread or the seal material to go in.

Air Supply

A Warning

1. Types of fluid

This product is designed for use with compressed air. Consult SMC if a different fluid is to be used.

Consult SMC regarding products for use with general purpose fluids, to confirm which fluids can be used.

2. When there is a large amount of drainage.

Compressed air containing a large amount of drainage can cause the malfunction of pneumatic equipment. An air dryer or Drain Catch should be installed upstream from filters.

3. Drain management

If air filter drains are not flushed regularly, the drainage will flow downstream leading to the malfunction of pneumatic equipment.

In cases where the management of drain flushing will be difficult, the use of filters with automatic drains is recommended.

For details on the quality of compressed air mentioned above, refer to SMC's "Best Pneumatics" catalogue vol. 4.

Operating Environment

$oldsymbol{\Delta}$ Warning

- 1. Do not operate in locations in an explosive atmosphere.
- 2. Do not operate in locations where vibration or impact occurs.
- 3. In locations near heat resources, block off radiant heat.

Maintenance

$oldsymbol{\Lambda}$ Caution

- Check for the following during regular maintenance, and replace components as necessary.
 - a) Scratches, gouges, abrasion, corrosion
 - b) Leakage
 - c) Twisting, flattening or distortion of tubing
 - d) Hardening, deterioration or softness of tubing
- 2. Do not repair or patch the replaced tubing or fittings for reuse.
- 3. When using insert or miniature fittings over a long period, some leakage may occur due to age deterioration of the materials. Perform periodic inspections, and if any leakage is detected, correct the problem by additional tightening. If tightening becomes ineffective, replace the fittings with a new product immediately.

Polyurethane Coil Tubing


Series TCU



RoHS

For flexible tubing Compact piping possible

Burst Pressure Characteristics Curve




Specifications

Model	TCU 0425B-1	TCU 0425B-2	TCU 0425B-3	TCU 0604B-1	TCU 0604B-2	TCU 0604B-3	TCU 0805B-1	
Number of tubes	1	2	3	1	2	3	1	
Tube O.D. (mm)		4			6			
Tube I.D. (mm)		2.5		4			5	
Fluid	Air (1)							
Max. operating pressure (2)			0.8	MPa at 20	°C			
Burst pressure		Refe	er to press	ure charac	teristics cu	ırve.		
Operating temperature	−20 to +60 °C							
Material	Polyurethane							
Colour				Black				

Note 1) Consult SMC if using for other fluids than air.

Note 2) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.

Dimensions



330

Dimensions are changeable due to material.

Made to Order -(Consult SMC for detailed specifications, dimensions and delivery.) Change of coil turns, Color change (Max. operating length) 100 100 ØĎ Tube fastener (Multi-tube only)

Spec.	Tube size	Tube size (mm)		(mm)			Max. operating	
Part No.	O.D.	I.D.	L	øD	tubes per tube length		length (mm)	
TCU0425□-1-N-X6			N X 4	18	1	3 to 90	L X 5.9 + 200	
TCU0425□-2-N-X6	4	2.5	N X 8	28	2	3 to 90	L X 4.4 + 200	
TCU0425□-3-N-X6			N X 12	28	3	3 to 63	L X 2.9 + 200	
TCU0604□-1-N-X6			N X 6	24	1	3 to 90	L X 5.3 + 200	
TCU0604□-2-N-X6	6	4	N X 12	37	2	3 to 66	L X 3.8 + 200	
TCU0604□-3-N-X6			N X 18	37	3	3 to 44	L X 2.5 + 200	

Spe	ec.	Tube siz	Tube size (mm)		(mm)			Max. operating
Part No.	\	O.D.	I.D.	L	øD	tubes	per tube length	length (mm)
TCU0805□-1-N]-X6	0	5	N X 8	31	1	3 to 90	L X 5.2 + 200
TCU0805□-2-N	-X6	8	5	N X 16	16 42 2 3	3 to 40	L X 3 + 200	
TCU1065□-1-N	-X6	10	0.5	N X 10	52	1	3 to 45	L X 5 + 200
TCU1065□-2-N	-X6	10	6.5	N X 20	52	2	3 to 35	L X 3 + 200
TCU1208□-1-N	-X6	12	8	N X 12	67	1	3 to 35	L X 5 + 200
TCU1208□-2-N]-X6		ð	N X 24	67	2	3 to 30	L X 3 + 200

^{□ →} B (Black), W (White), R (Red), BU (Blue), Y (Yellow), G (Green), C (Clear), YR (Orange)



N → Coil turns


Polyurethane Flat Tubing

Series TFU



Compact piping possible

Burst Pressure Characteristics Curve



Specifications

-						
Part No.	TFU 0425B-2	TFU 0425B-3	TFU 0604B-2	TFU 0604B-3	TFU 0805B-2	TFU 0805B-3
Number of tubes	2	3	2	3	2	3
Tube O.D. (mm)	4	ļ	(6	8	3
Tube I.D. (mm)	2.	5	4	1	ŧ	5
Fluid	Air ⁽¹⁾					
Max. operating pressure (2)			0.8MPa	at 20°C		_
Burst prssure		Refer to b	urst pressur	e characteris	stics curve	
Operating temprature		-:	20 to +60°C	(No freezing	g)	
Material			Polyur	ethane		
Colour	Black					
Min. bending radius (mm)	1	0	1	5	2	0
Tube length per roll (m)	10					


Note Note:

Note1) Consult SMC if using for other fluids than air.

Note2) Refer to burst pressure characteristics curve for other temperatures.

Avoid abnormal temperature rises.

How to Order



Made to Order

(Consult SMC for detailed specifications, dimensions and delivery.)

1 Colour change (10m roll)

Suffix "X4" to the end of part number. Ex.) TFU0604BU-2-10-X4


• W: White, R: Red, BU: Blue, Y: Yellow, G: Green, C: Clear, YR: Orange (All tubes are same colour.)

② Longer roll length (50m or 100m roll)

Suffix "X3" to the end of part number. Ex.) TFU0425B-2-50-X3

3 Number of tubes (10m roll)

Suffix "X4" to the end of part number. Ex.) TFU0604B-4-10-X4



Flame Resistance (Equivalent to UL-94 Standard V-0)

FR Soft Nylon Tubing

Series TRS




RoHS

Applicable for general air pressure and water in a spark atomosphere such as spot welding.

Flame resistance tube

Burst Pressure Characteristics Curve




Series Table			● : 20m roll	□: 100m roll			
Model	TRS0603	TRS0805	TRS1065	TRS1208			
Tube O.D. (mm)	6	8	10	12			
Tube I.D. (mm)	3	5	6.5	8			
Black (B)							
White (W)				•			
Red (R)			•	•			
Blue (BU)		<u> </u>		•			
Green (G)		•	•	•			
Specifications							
Fluid		Air, V	Vater				
Max. operating pressure		1.2MPa	at 20°C				
Burst pressure	Refer	to burst pressure	e characteristics	curve.			
Min. bending radius (mm)	17	19	27	32			
Operating temperature	-20 to	o +60°C (Water: 0	to 60°C)(No free	ezing)			
Material	Flame	Flame resistance nylon (UL-94 Standard V-0)					

⚠ Precautions

⚠ Caution

①Applicable for general industry water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure. If exceeding that value, fitting may be damaged and tubing may be burst.

- ②The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises which may burst the tubing.
- 3The value of the min. bending radius is at a temperature of 20°C and O.D. variable rate 10% max. In case that operating temperature is higher than 20°C, O.D. variable rate may be over 10% even if bending radius is within the specified range.





Flame Resistance (Equivalent to UL-94 Standard V-0)

FR Double Layer Tubing

Series TRB ROHS




Suitable for air and water piping in environments where sparks from spot welders, etc., may be a problem. Double layer design using flame resistant resin (equivalent to UL-94 Standard V-0) for outer layer.



Series	Table			●: 20m roll	□: 100m roll
Model		TRB0604	TRB0806	TRB1075	TRB1209
Inner tub	e O.D. (mm)	6	8	10	12
Inner tub	e I.D. (mm)	4	6	7.5	9
Outer lay	er thickness (mm)	1	1	1	1
	Black (B)	<u> </u>			
	White (W)	—	•	<u> </u>	•
Outer	Red (R)	•	<u> </u>	<u> </u>	<u> </u>
layer colour	Blue (BU)		<u> </u>	<u> </u>	•
	Yellow (Y)		<u> </u>	<u> </u>	•
	Green (G)		<u> </u>	<u> </u>	<u> </u>
	mum bending (4) us (mm)	15	28	35	45

Specifications






Note1) The colour of all inner tube is black.


Note2) Applicable for general industry water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure.

Note3) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.

Note4) The value for a temperature of 20°C and O.D.variable rate 10% max.

Inner tube Outer layer FR double layer tubing (sectional view)






FR Double Layer Tubing Series TRB

How to Install to One-touch Fitting

⚠ Caution

Length of tube to be inserted into One-touch fitting is indicated on the outer layer of TRB tubing.

Cut the tube according to this indication. (Procedure ①) and then strip off the outer layer. (Procedure ②) for installing tube.



Strip off outer layer

A Precautions

⚠ Caution

- ①Applicable for general industrial water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure. If exceeding that value, fitting may be damaged and tubing may be burst.
- ②The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises which may burst the tubing.
- 3The value of the min. bending radius is at a temperature of 20°C and O.D. variable rate 10% max. In case that operating temperature is higher than 20°C, O.D. variable rate may be over 10% even if bending radius is within the specified range.




Flame Resistant (Equivalent to UL-94 Standard V-0) FR Double Layer Polyurethane tubing

Series TRBU ROHS







Series Table



	Model	TRBU0604	TRBU0805	TRBU1065	TRBU1208
Inter	nal tube O.D. mm	6	8	10	12
Inter	nal tube I.D. mm	4	5	6.5	8
Exte	rnal layer thickness mm	1	1	1	1
Note 1)	Black (B)	<u> </u>	<u> </u>		
^z 0	White (W)			<u> </u>	—
ayer	Red (R)			<u> </u>	—
la la	Blue (BU)			<u> </u>	—
External layer	Yellow (Y)			<u> </u>	—
û	Green (G)		•	<u> </u>	—
	Note 4)				
	nimum hond	5	20	27	35

Specifications

F	luid	Air, Water Note 2)				
Maximum operating Note 3) pressure (at 20°C)		0.8MPa {8.2kgf/cm²}				
Burst pressure		Refer to burst pressure characteristics curve				
Ambient au temperatur		-20 to 60°C For water 0 to 40°C (without freezing)				
Materials	Internal tube	Polyurethane				
waterials	External layer	Polyolefin (equivalent to UL-94 standard V-0)				


Note 1) The colour of all internal tubes is black.


Note 2) Can be used with general industrial water. Contact SMC if used with other fluids. Also keep surge pressure at or below the maximum operating pressure.

Note 3) In case of other temperatures, refer to the burst pressure characteristics curve. In addition, operate so that abnormal temperature rise due to adiabatic compression does not occur.

Note 4) Indicates the bending value of the tubing at a temperature of 20 $^{\circ}\text{C}.$

Burst Pressure Characteristics Curve and Operating Pressure






Installation on One-touch Fittings

⚠ Caution

Since the pitch length for installation on a One-touch fitting is indicated on the external layer of TRBU tubing, cut the tubing according to this indication (Step 1), strip off the external layer only (Step 2), and then install on the One-touch fitting.



Precautions on Useage

⚠ Caution

- Useage is possible with general industrial water. Contact SMC if product will be used with other fluids. Also, keep surge pressure at or below the maximum operating pressure. If surge pressure exceeds the maximum operating pressure, this can cause damage to fittings or bursting of the tubing.
- The maximum operating pressure is the value when at 20°C. In case of other temperatures, refer to the burst pressure characteristics curve. Furthermore, bursting of the tubing can be caused by an abnormal temperature rise due to adiabatic compression.
- 3. The minimum bend radius indicates the bending value of the tubing at a temperature of 20°C. The tubing may bend beyond the minimum bend radius at higher temperatures.
- 4. Tubing should be stored in a location out of direct sunlight and at 40°C or below.



Antistatic Tubing

Series TA RoHS

Conductive tubing prevents troubles caused by static electricity.


Antistatic soft nylon tubing/Series TAS

For air pressure piping to product or assembly while preventing static electricity.

Flame resistant tube (UL-standard, V-0)




Burst Pressure Characteristics Curve



Series Table				●:2	0m roll □:	100m roll
Model	TAS3222	TAS0425	TAS0604	TAS0805	TAS1065	TAS1208
Tube O.D. (mm)	3.2	4	6	8	10	12
Tube I.D. (mm)	2.2	2.5	4	5	6.5	8
Black (B)	—					
Specifications Max. operating pressure (1)			1.2MPa a	1 20°C		
Burst pressure	ı	Refer to burs	st pressure o	haracteristic	cs curve.	
Min. bending radius (mm) (2)	12	12	15	19	27	32
Operating temperature	0 to 40°C					
Material	Conductive nylon + Flame resistant nylon (UL-94standard, V-0)					
Surface resistance			10 ⁴ to 1	$0^7\Omega$		•

Note1) Refer to burst pressure characteristics curve for other temperatures.
Avoid abnormal temperature rises.
Note2) The value at temperature of 20°C and O.D. variable rate 10% max.

How to Order




Antistatic polyurethane tubing/Series TAU

For air pressure piping to product or assembly while preventing static electricity.

Flexible tube



Burst Pressure Characteristics Curve



Series Table ●: 20m roll Model TAU3220 TAU0425 TAU0604 TAU0805 TAU1065 TAU1208 Tube O.D. (mm) 3.2 10 12 Tube I.D. (mm) 2.5 6.5 Black (B) Specifications Max. operating pressure (1) 0.9MPa at 20°C Burst pressure Refer to burst pressure characteristics curve Min. bending radius (mm)(2) 10 35 0 to 40°C Operating temperature Material Conductive polyurethane Surface resistance 10^4 to $10^7\,\Omega$

Note1) Refer to burst pressure characteristics curve for other temperatures.

Avoid abnormal temperature rises.

Note2) The value at temperature of 20°C.

